



PRODUCT DATA SHEET

Raffex 120 ACB[®]

PROPERTY	ASTM METHOD	MIN	TYPICAL	MAX
API Gravity	D287	8.5	9.5	11
Density, lb/gal @ 60F	D1250	8.270	8.358	8.418
Viscosity, SUS @ 100F	D2161		12400	
Viscosity, SUS @ 210F	D2161	100	120	140
Viscosity, cSt @ 100C	D445		22	
Flash, COC, F	D92	405	420	
Pour Point, F	D97		60	
Color	D1500		D8.0	
Mixed Aniline Point, F	D611		98	
Sulfur, w%	D2622		1.12	
Clay-Gel Analysis, w%	D2007			
Asphaltenes			Nil	0.1
Polar Compounds			21	
Aromatics		55	65	
Saturates			14	20
Carbon-Type Analysis, %	D2140			
Ca			42	
Cn			36	
Cp			22	

SJR makes no warranty, either expressed or implied, with respect to the products fitness for a particular purpose. User shall determine suitability of the product for the intended application and assume all risk.