



TRICOR REFINING, LLC

Producers of GOLDEN BEAR PRESERVATION PRODUCTS

1134 Manor St. • Oildale, CA 93308 / P.O. Box 5877 • Bakersfield, CA 93388
 Phone 661.393.7110 – Fax 661.393.1601

RECLAMITE® Asphalt Rejuvenating Agent

Specifications:

Tests	Test Method		Requirements	
	ASTM	AASHTO	Min.	Max.

Tests on Emulsion:

Viscosity @ 25°C, SFS	D-244	T-59	15	40
Residue, % w ⁽¹⁾	D-244 (mod)	T-59 (mod)	60	65
Miscibility Test ⁽²⁾	D-244 (mod)	T-59 (mod)	No Coagulation	
Sieve Test, % w ⁽³⁾	D-244 (Mod)	T-59 (mod)	---	0.1
Particle Charge Test	D-244	T-59	Positive	
Percent Light Transmittance ⁽⁴⁾	GB	GB	---	30
Cement Mixing	D-244			2.0

Tests on Residue from Distillation

Flash Point, COC, °C	D-92	T-48	196	---
Viscosity @ 60°C, cSt	D-445	---	100	200
Asphaltenes, %w	D-2006-70	---		0.75
Maltene Distribution Ratio	D-2006-70	---	0.3	0.6
PC + A ₁ ⁽⁵⁾				
S + A ₂				
PC/S Ratio ⁽⁵⁾	D-2006-70	---	0.5	---
Saturate hydrocarbons, S ⁽⁵⁾	D-2006-70	---	21	28

¹ASTM D-244 Evaporation Test for percent of residue is made by heating 50 gram sample to 149°C (300°F) until foaming ceases, then cool immediately and calculate results.

²Test procedure identical with ASTM D-244 60 except that .02 Normal Calcium Chloride solution shall be used in place of distilled water..

³Test procedure identical with ASTM D-244 60 except that distilled water shall be used in place of two percent sodium oleate solution.

⁴Test procedure is attached.

⁵Chemical composition by ASTM Method D-2006-70:

PC = Polar Compounds, A₁ = First Acidaffins.
 A₂ = Second Acidaffins, S = Saturated Hydrocarbons.

Note: For gal/ton conversion use 242 gal/ton.

Note: Data presented are typical. Slight variation may occur from lot to lot.