TRICOR REFINING, LLC
Producers of GOLDEN BEAR PRESERVATION PRODUCTS

1134 Manor St. • Oildale, CA 93308 / P.O. Box 5877 • Bakersfield, CA 93388
Phone 661.393.7110 – Fax 661.393.1601

PRODUCT SPECIFICATION
SS-1H ASPHALT EMULSION

TESTS (ASTM Unless Otherwise Stated)	TYPICAL TEST	MANUFACTURING SPECIFICATION		GUARANTEED SPECIFICATION	
		Min	Max	Min	Max
Viscosity SSF @ 25 deg. C sec D-244		20	100	20	100
Settlement 5 Day, % D-244			5		5
Storage Stability Test 1 Day % D-244			1		1
Cement Mixing Test % D-244			2.0		2.0
Residue by Distillation W%	60	57		57	
Penetration @ 25 deg. C		40	90	40	90
Ductility,25 deg. C, 50 mm/min, mm		400		400	
Solubility in Trichloroethylene, %		97.5		97.5	

July 23, 2012