



1134 Manor St. • Bakersfield, CA 93308 / P.O. Box 5877 • Bakersfield, CA 93388  
 Phone 661.393.7110 – www.tricorrefining.com

### Cyclogen® ME Specification

<b>Tests (All Tests ASTM Unless Otherwise Stated)</b>		<b>Typical Test</b>	<b>Specification</b>	
			<b>Min.</b>	<b>Max.</b>
VISCOSITY, 25C, SSF	D-244	38.0	25.0	150
SIEVE, W%	D-244	0.01		0.10
RESIDUE, W%	D-244	61.0	60.0	
VISCOSITY, 60 C, CST		2268	1000	4000
PARTICLE CHARGE TEST	D-244	POS	POS	
PH OF EMULSION	D-244	5.4		
CEMENT MIXING TEST	D-244	PASS	NIL	2.00